

# Efka<sup>®</sup> FL 3777

(old : Efka<sup>®</sup> 3777 N)

## general

slip and leveling agent

- improves leveling
- prevents cratering
- helps substrate wetting
- acts as a defoamer and de-aeration aid
- does not interfere with intercoat adhesion

## chemical nature

fluorocarbon-modified polymer

---

## Properties

### physical form

clear, colorless liquid

### shelf life

The product should be stored in a cool dry place. When kept in its original unopened containers, it will keep up to 4 years.

### typical properties (no supply specification)

active ingredients	~ 70%
solvent	xylene
density at 20 °C (68 °F)	~ 0.98 g/cm <sup>3</sup>
flash point	25 °C (77°F)
color	≤ 1

---

## Application

Efka<sup>®</sup> FL 3777 is especially suitable for

- baking enamels based on alkyd, acrylic or polyester resins
- polyurethane coatings
- two-pack epoxy coatings
- air-drying alkyd systems

### recommended concentrations

0.5–2.0% on total formulation

Efka<sup>®</sup> FL 3777 should be added at the end of the batch preparation.

**Safety**

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

**Note**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted

BASF SE  
Formulation Additives  
67056 Ludwigshafen, Germany  
[www.dispersions-pigments.basf.com](http://www.dispersions-pigments.basf.com)  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)